

TRAFFIC PAINT TEST REPORT

Project No.: EA16048



Attn: Mr. Joe Filice R.E.T.

To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3

Distribution Addressee: AMEC Environment & Infrastructure
 5671 - 70 Street
 Edmonton, AB
 Canada T6B 3P6
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599

Formulation:		Supplier: ENNIS									
White Alkyd 986061		Tests Required									
Lab Sample Number	Batch Number	Relative Density Lb/Gal (25/25°C)	Viscosity (Krebs)	Colour	Dry to Traffic (Minutes)	Non-Volatile Content (%)	Pigment Content (%)	Date Sampled 2014	Date Received 2014	Date Reported 2014	Applicator and Location
					Batch						
B38	CPP1403W0064	12.03	76.6			71.5	55.9	Jun-28	Jul-7	Jul-10	Deerfoot Trail Calgary, AAA Striping
B71	CPP1405W0523	12.26	94.0 *			73.8	56.9	N/A	Aug-15	Aug-19	Deerfoot Trail Calgary, AAA Striping
Tolerance Limits											
2014	986061										
Tolerance Limits											
Upper Limit			85.0				58.0				
Lower Limit		11.0	70.0			68.0					

Notes : City of Calgary Specification

* Indicates result outside tolerance limits.
 Test not Required by AT

PER _____
 DATE _____
 Reviewed By: _____

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.