

TRAFFIC PAINT TEST REPORT

Project No.: EA16048



Attn: Mr. Joe Filice R.E.T.

To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3

Distribution Addressee: AMEC Environment & Infrastructure
 5671 - 70 Street
 Edmonton, AB
 Canada T6B 3P6
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599

Formulation:		Supplier: ENNIS									
Yellow Alkyd 986063		Tests Required									
Lab Sample Number	Batch Number	Relative Density Lb/Gal (25/25°C)	Viscosity (Krebs)	Colour	Dry to Traffic (Minutes)	Non-Volatile Content (%)	Pigment Content (%)	Date Sampled	Date Received	Date Reported	Applicator and Location
	2014				Batch						
B37	CPP1405Y0547	11.37	70.7			73.5	54.8	Jun-28	Jul-7	Jul-10	Deerfoot Trail Calgary, AAA Striping
B72	CPP1405Y0547	11.45	79.5			71.5	54.7	N/A	Aug-15	Aug-19	Deerfoot Trail Calgary, AAA Striping
Tolerance Limits											
2014	986063										
Tolerance Limits											
Upper Limit			85.0				58.0				
Lower Limit		11.0	70.0			68.0					

Notes : City of Calgary Specification

* Indicates result outside tolerance limits.

Test not Required by AT

PER _____
 DATE _____

Reviewed By: _____

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.