

TRAFFIC PAINT TEST REPORT

Project No.:EA16450



Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3

Distribution Addressee: WSP Canada Limited
 5671 - 70 Street
 Edmonton, AB
 Canada T6B 3P6
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599

Formulation:		Supplier: Cloverdale							
White WB 62352		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch	Date Sampled	Date Received	Applicator and Location
	2024						2021	2021	
B41	524C8772	1.602	82.2	76.8	60.9	3.0	Jun-23	Jul-15	Line King No Location Con#20500
B43	524C8775	1.588*	79.3*	76.6	60.5	3.0	Jun-25	Jul-15	Line West Hwy 8 to OBCR
Tolerance Limits									
2023	White 62352	1.653	85	77.2	60.8	2.9			
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.703	90	79.2	62.8				
Lower Limit		1.603	80	75.2	58.8				

Batch numbers B41 and B43 do not match any current Received manufacture

* Indicates result outside tolerance limits.

 Test not Required by AT

PER:  **Jul-29**
 DATE

Reviewed By: _____

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.

TRAFFIC PAINT TEST REPORT

Project No.:EA16450



Attn: Rishi Adhikari, P.Eng.


To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3

Distribution Addressee: WSP Canada Limited
 5671 - 70 Street
 Edmonton, AB
 Canada T6B 3P6
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599

Formulation:		Supplier: Cloverdale							
White WB 62352		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch	Date Sampled	Date Received	Applicator and Location
B85	8773	1.605	86.0	77.6	61.6	3.3	Sep-3	Sep-5	Line King Hwy 12:10 Con#23051
Tolerance Limits									
2023	White 62352	1.653	85	77.2	60.8	2.9			
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.703	90	79.2	62.8				
Lower Limit		1.603	80	75.2	58.8				

Batch numbers B85 and B86 do not match any current Received manufacture

* Indicates result outside tolerance limits.

 Test not Required by AT

PER:  **Sep-16**
 DATE

Reviewed By: _____

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.

TRAFFIC PAINT TEST REPORT

Project No.:EA16450



Attn: Rishi Adhikari, P.Eng.


To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3


Distribution Addressee: WSP Canada Limited
 5671 - 70 Street
 Edmonton, AB
 Canada T6B 3P6
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599

Formulation: White WB 62352		Supplier: Cloverdale							
		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch	Date Sampled	Date Received	Applicator and Location
B116	S24C8777	1.499*	87.9	77.1	60.8	3.9	Sep-23	Sep-25	Line King Hwy 835:04 from Jct Hwy 12 of North Hwy 601Con#23051
Tolerance Limits									
2023	White 62352	1.653	85	77.2	60.8	2.9			
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.703	90	79.2	62.8				
Lower Limit		1.603	80	75.2	58.8				

Batch numbers B116 and B117 do not match any current Received manufacture

* Indicates result outside tolerance limits.

 Test not Required by AT

PER:  **1-Oct-24**
 DATE

Reviewed By: _____

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.