

TRAFFIC PAINT TEST REPORT

Project No.:EA16450




Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3

Distribution Addressee: WSP Canada Limited
 5671 - 70 Street
 Edmonton, AB
 Canada T6B 3P6
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599

Formulation: Yellow WB 62353		Supplier: Cloverdale							
		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch	Date Sampled	Date Received	Applicator and Location
B32	S24E9201	1.608	81	76.9	59.2	2.9	Jun-24	Jul-2	Line West Hwy 640:02 Con#21931
Tolerance Limits									
2023	Yellow 62353	1.610	80.4	76.5	58.6	2.8			
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.660	85.4	78.5	60.6				
Lower Limit		1.560	75.4	74.5	56.6				

* Indicates result outside tolerance limits.

 Test not Required by AT

PER:  Jul-15
 DATE

Reviewed By: _____

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.

TRAFFIC PAINT TEST REPORT

Project No.:EA16450



Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3

Distribution Addressee: WSP Canada Limited
 5671 - 70 Street
 Edmonton, AB
 Canada T6B 3P6
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599

Formulation:		Supplier: Cloverdale							
Yellow WB 62353		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch	Date Sampled	Date Received	Applicator and Location
	2024						2021	2021	
B42	524C8777	1.621	81.7	77.0	59.5	2.9	Jun-23	Jul-15	Line King No Location Con#20500
B44	524E92001	1.631	81.2	77.0	59.3	2.9	Jun-25	Jul-15	Line West Hwy 8 to OBCR
Tolerance Limits									
2023	Yellow 62353	1.610	80.4	76.5	58.6	2.8			
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.660	85.4	78.5	60.6				
Lower Limit		1.560	75.4	74.5	56.6				

Batch numbers **B42** and **B44** do not match any current Received manufacture

* Indicates result outside tolerance limits.



Test not Required by AT

PER: _____ **Jul-29**
 DATE
 Reviewed By: _____

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.

TRAFFIC PAINT TEST REPORT

Project No.:EA16450



Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3

Distribution Addressee: WSP Canada Limited
 5671 - 70 Street
 Edmonton, AB
 Canada T6B 3P6
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599

Formulation: Yellow WB 62353		Supplier: Cloverdale							
		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch	Date Sampled	Date Received	Applicator and Location
B86	2024 8777	1.560	83.0	77.0	59.5	3.1	2021 Sep-3	2021 Sep-5	Line King Hwy 12:10 Con#23051
Tolerance Limits									
2023	Yellow 62353	1.610	80.4	76.5	58.6	2.8			
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.660	85.4	78.5	60.6				
Lower Limit		1.560	75.4	74.5	56.6				

Batch numbers B85 and B86 do not match any current Received manufacture

* Indicates result outside tolerance limits.

Test not Required by AT

PER: **Sep-16**
 DATE

Reviewed By: _____

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.

TRAFFIC PAINT TEST REPORT

Project No.:EA16450



Attn: Rishi Adhikari, P.Eng.


To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3


Distribution Addressee: WSP Canada Limited
 5671 - 70 Street
 Edmonton, AB
 Canada T6B 3P6
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599

Formulation: Yellow WB 62353		Supplier: Cloverdale							
		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch	Date Sampled	Date Received	Applicator and Location
B117	S24C8772	1.460*	77.0	75.5	57.8	3.1	Sep-23	Sep-25	Line King Hwy 835:04 from Jct Hwy 12 of North Hwy 601Con#23051
Tolerance Limits									
2023	Yellow 62353	1.610	80.4	76.5	58.6	2.8			
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.660	85.4	78.5	60.6				
Lower Limit		1.560	75.4	74.5	56.6				

Batch numbers B116 and B117 do not match any current Received manufacture

* Indicates result outside tolerance limits.

 Test not Required by AT

PER:  **01-Oct-24**
 DATE

Reviewed By: _____

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.