

TRAFFIC PAINT TEST REPORT

Project No.: 16450



Attn: Rishi Adhikari, P.Eng.

Distribution Addressee: WSP Canada Limited

To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3

5671 - 70 Street
 Edmonton, AB
 Canada T6B 3P6
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599

Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599

Formulation: White KW-29		Supplier: ISP							
		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch	Date Sampled	Date Received	Applicator and Location
	2024						2024	2024	
B102	P-7	1.671	79.3	78.2	61.9	3.3	N/A	Sep-21	AAA Hwy 2:50 Con#24231
B106	P-7	1.633	77.4	77.2	61.7	3.6	Sep-9	Sep-13	AAA Hwy 744:04 from Km 10:520 to Km 38:340 Con#24538
Tolerance Limits									
2023	KW-29	1.676	76.2	78.6	61.7	3.5			
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.726	81.2	80.6	63.7				
Lower Limit		1.626	71.2	76.6	59.7				

* Indicates result outside tolerance limits.



Test not Required by AT

PER: _____ **23-Sep-24**
 DATE

Reviewed By: _____

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.

TRAFFIC PAINT TEST REPORT

Project No.: 16450



Attn: Rishi Adhikari, P.Eng.

Distribution Addressee: WSP Canada Limited

5671 - 70 Street

Edmonton, AB

Canada T6B 3P6

Tel +1 (780) 436-2152

Fax +1 (780) 377-3599

Tel +1 (780) 436-2152

Fax +1 (780) 377-3599

To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3

Supplier: **ISP**

Tests Required

Formulation: White KW-29		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch	Date Sampled	Date Received	Applicator and Location
B142	P-7	1.689	74.2	78.3	61.2	3.7	Sep-30	Oct-17	AAA Hwy 750:04
Tolerance Limits									
2023	KW-29	1.676	76.2	78.6	61.7	3.5			
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute	+2			
Upper Limit		1.726	81.2	80.6	63.7	5.5			
Lower Limit		1.626	71.2	76.6	59.7	N/A			

* Indicates result outside tolerance limits.



Test not Required by AT

PER: _____ **28-Oct-24**
 DATE

Reviewed By: _____

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.