## TRAFFIC PAINT TEST REPORT

Project No.: 16335

Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation
Technical Standards Branch
2nd Floor, Twin Atria Building
4999 - 98 Ave
Edmonton, AB T6B 2X3

Distribution Addressee: WSP Canada Limited 5671 - 70 Street Edmonton, AB Canada T6B 3P6

> Tel +1 (780) 436-2152 Fax +1 (780) 377-3599

Tel +1 (780) 436-2152 Fax +1 (780) 377-3599

Supplier: **OZARK** Formulation: White WB 17251B **Tests Required** Lab Batch Relative Viscosity **Pigment** Date Applicator and Location Non-Dry to Date Sample Number Density Volatile Content Touch Received Sampled 2024 Number 2024 Content (Minutes) 2024 (25/25°C) (Krebs) (%) (Minutes) (%) **B1** 040324WD0041 1.561\* 65.0\* 71.2\* 57.9\* 3.5 Volker Stevin CMA6 Pincher Greek, AB May-9 May-27 Tolerance Limits 2023 17251B 1.663 82 75.7 62.8 ± 2% **Tolerance Limits** ± 2%  $\pm 0.05$ ± 5 absolute absolute **Upper Limit** 1.713 87 77.7 64.8 Lower Limit 1.613 77 73.7 60.8

\* Indicates result outside tolerance limits.

Test not Required by AT

PER:

Reviewed By:

Reporting of these results constitutes a testing service only.

Engineering Interpretation or evaluation of the test results is provided only on written request.

wsp

## TRAFFIC PAINT TEST REPORT

Project No.: 16335

usp

Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation
Technical Standards Branch
2nd Floor, Twin Atria Building
4999 - 98 Ave
Edmonton, AB T6B 2X3

Distribution Addressee: WSP Canada Limited 5671 - 70 Street Edmonton, AB Canada T6B 3P6 Tel +1 (780) 436-2152 Fax +1 (780) 477-3599

Tel +1 (780) 436-2152 Fax +1 (780) 377-3599

Formulation:		Supplier:		OZARK	<u></u>				
White WB 17251B		Tests Required							
Lab	Batch	Relative	Viscosity	Non-	Pigment	Dry to	Date	Date	Applicator and Location
Sample	Number	Density		Volatile	Content	Touch	Sampled	Received	
Number	2024	(25/25°C)	(Krebs)	Content (%)	(%)	(Minutes) (Minutes)	2024	2024	
B3	011624WD0008	1.554*	78.2	75.1	61.3	3.7	May-29	May-30	EMCON Hwy 21:26, 12:611-23:773 CMA9 Sampler Ryan Luider 780-644-2822
B5	011924WD0011	1.613	76.4*	74.5	60.8	3.3	May-27	May-31	Emcon Hwy 2:40 Sampler Athur Kavulok 780-675-2780
			Toleranc	e Limits					
2023	17251B	1.663	82	75.7	62.8				
Tolerance Limits				± 2%	± 2%				
		± 0.05	± 5	absolute	absolute				
Upper Limit		1.713	87	77.7	64.8				
Lower Limit		1.613	77	73.7	60.8				

\* Indicates result outside tolerance limits.

Test not Required by AT

PER:

Reviewed By:

Reporting of these results constitutes a testing service only.

Engineering Interpretation or evaluation of the test results is provided only on written request.