

**TRAFFIC PAINT TEST REPORT**

Project No.: 16335



Attn: Rishi Adhikari, P.Eng.

Distribution Addressee: WSP Canada Limited

5671 - 70 Street

Edmonton, AB

Canada T6B 3P6

Tel +1 (780) 436-2152


Fax +1 (780) 377-3599


To: Alberta Transportation  
 Technical Standards Branch  
 2nd Floor, Twin Atria Building  
 4999 - 98 Ave  
 Edmonton, AB T6B 2X3

Tel +1 (780) 436-2152

Fax +1 (780) 377-3599

Formulation: Yellow WB 27251		Supplier: <b>OZARK</b>							
Tests Required									
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch (Minutes)	Date Sampled	Date Received	Applicator and Location
<b>B2</b>	051623YD0081	1.684	82.3	79.1	63.5	3.1	May-9	May-27	Volker Stevin CMA6 Pincher Greek, AB
Tolerance Limits									
<b>2021</b>	<b>27251</b>	<b>1.673</b>	<b>82.3</b>	<b>77.8</b>	<b>62.2</b>				
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.723	87.3	79.8	64.2				
Lower Limit		1.623	77.3	75.8	60.2				

\*Note:  \* Indicates result outside tolerance limits.

 Test not Required by AT

PER: \_\_\_\_\_ **30-May-24**  
 DATE

Reviewed By: \_\_\_\_\_

Reporting of these results constitutes a testing service only.  
 Engineering Interpretation or evaluation of the test results is provided only on written request.