

TRAFFIC PAINT TEST REPORT

Project No.: EA16450




Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3

Distribution Addressee: WSP Canada Limited
 5671 - 70 Street
 Edmonton, AB
 Canada T6B 3P6
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599

Formulation:		Supplier: PPG							
White WB 985221		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch (Minutes)	Date Sampled	Date Received	Applicator and Location
B126	CPP2305W0507	1.541	74.2	74.8	60.5	3.5	Sep-28	Oct-1	Lafrentz Hwy 685:05 Con#020539
Tolerance Limits									
985221									
Tolerance Limits									
Upper Limit									
Lower Limit									

* Indicates result outside tolerance limits.
 Test not Required by AT

Note: B126 Paint Formulation is not on Alberta Transportations approved list.

PER: _____ **8-Oct-24**
 DATE
 Reviewed By: _____

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.