

**TRAFFIC PAINT TEST REPORT**

Project No.: EA16450



Attn: Rishi Adhikari, P.Eng.


To: Alberta Transportation  
 Technical Standards Branch  
 2nd Floor, Twin Atria Building  
 4999 - 98 Ave  
 Edmonton, AB T6B 2X3

Distribution Addressee: WSP Canada Limited  
 5671 - 70 Street  
 Edmonton, AB  
 Canada T6B 3P6  
 Tel +1 (780) 436-2152  
 Fax +1 (780) 377-3599

Formulation:		Supplier: PPG							
White Acetone 986061		Tests Required							
Lab	Batch	Relative	Viscosity	Non-	Pigment	Dry to	Date	Date	Applicator and Location
Sample Number	Number	Density	(Krebs)	Volatile Content (%)	Content (%)	Touch	Sampled	Received	
	2024	(25/25°C)		(%)	(%)		2024	2024	
<b>B7</b>	CPP2403W0193	1.480	89.5	76.1	57.7	1.3	May-27	May-31	Lafrentz Hwy 2:64 Con#769909
<b>B9</b>	CPP2403W0190	1.488	85.1	75.6	57.8	1.2	May-29	May-30	Line West Hwy 791:05 Con#23278
<b>Tolerance Limits</b>									
	<b>986061</b>	<b>N/A</b>	<b>N/A</b>	<b>N/A</b>	<b>N/A</b>				
Tolerance Limits			± 5	± 2% absolute	± 2% absolute				
Upper Limit			90	76.0	57.5				
Lower Limit		1.35	75	71.0	52.0				

\*Note:

**Batch numbers do not match any current Received manufacture**

\* Indicates result outside tolerance limits.  
 Test not Required by AT

PER  **Jun-14**  
 DATE  
 Reviewed By: \_\_\_\_\_

Reporting of these results constitutes a testing service only.  
 Engineering Interpretation or evaluation of the test results is provided only on written request.

