

TRAFFIC PAINT TEST REPORT

Project No.: EA16450




Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3

Distribution Addressee: WSP Canada Limited
 5671 - 70 Street
 Edmonton, AB
 Canada T6B 3P6
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599

Formulation:		Supplier: PPG							
Yellow Acetone 986063		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch	Date Sampled	Date Received	Applicator and Location
	2024						2024	2024	
B8	CPP2310Y0972	1.412	81.7	74.5	52.9	1.1	May-27	May-31	Lafrentz Hwy 2:64 Con#769909
B10	CPP2403Y0194	1.414	79	75.2	53.1	1.1	May-29	May-30	Line West Hwy 791:05 Con#23278
Tolerance Limits									
	986063	N/A	N/A	N/A	N/A				
Tolerance Limits				± 2% absolute	± 2% absolute				
Upper Limit		1.45	90	75.0	55.0				
Lower Limit		1.32	75	70.0	49.0				

*Note:  Test not Required by AT * Indicates result outside tolerance limits.

PER:  **Jun-14**
 DATE

Reviewed By: _____

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.

