

TRAFFIC PAINT TEST REPORT

Project No.: EA16450




Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3

Distribution Addressee: WSP Canada Limited
 5671 - 70 Street
 Edmonton, AB
 Canada T6B 3P6
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599

Formulation: White WB EF-61-0140		Supplier: PPG Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch (Minutes)	Date Sampled	Date Received	Applicator and Location
B31	CPP2404W0331	0.658	77.5	78.8	61.2	3.1	Jun-24	Jul-2	Line West Hwy 640:02 Con#21931
Tolerance Limits									
2023	EF-61-0140	1.681	78	79	62.2				
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.731	83	81.0	64.2				
Lower Limit		1.631	73	77.0	60.2				

* Indicates result outside tolerance limits.

 Test not Required by AT

PER: _____ 15-Jul-24

Reviewed By: _____ DATE

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.

TRAFFIC PAINT TEST REPORT

Project No.: EA16450



Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3

Distribution Addressee: WSP Canada Limited
 5671 - 70 Street
 Edmonton, AB
 Canada T6B 3P6
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599

Formulation:		Supplier: PPG							
White WB EF-61-0140		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch (Minutes)	Date Sampled	Date Received	Applicator and Location
B136	CPP2407W0710	1.664	88.3	77.8	62.3	2.9	Sep-26	Oct-9	Line West Median Widening BeddingtonTr to Airport Trail Con#23525
2023	EF-61-0140	1.681	78	79	62.2	2.8			
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute	+2			
Upper Limit		1.731	83	81.0	64.2	4.8			
Lower Limit		1.631	73	77.0	60.2	N/A			

* Indicates result outside tolerance limits.



Test not Required by AT

PER: _____ 28-Oct-24

DATE

Reviewed By: _____

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.