

**TRAFFIC PAINT TEST REPORT**

Project No.: EA16450



Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation  
 Technical Standards Branch  
 2nd Floor, Twin Atria Building  
 4999 - 98 Ave  
 Edmonton, AB T6B 2X3

Distribution Addressee: WSP E&I Canada Limited  
 5671 - 70 Street  
 Edmonton, AB  
 Canada T6B 3P6  
 Tel +1 (780) 436-2152  
 Fax +1 (780) 377-3599

Formulation: Yellow WB EF-62-0124		Supplier: PPG							
		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch (Minutes)	Date Sampled	Date Received	Applicator and Location
	<b>2023</b>						2024	2024	
<b>B4</b>	CPP2308Y0828	1.453*	76.8*	76.0	55.6	3.6	May-29	May-30	EMCON Hwy 21:26, 12:611-23:773 CMA9 Sampler Ryan Luider 780-644-2822
<b>B6</b>	CPP2308Y0828	1.510	75.2*	75.8	56.7	2.9	May-27	May-31	Emcon Hwy 2:40 Sampler Athur Kavulok 780-675-2780
<b>Tolerance Limits</b>									
<b>2021</b>	<b>EF-62-0124</b>	<b>1.532</b>	<b>83.5</b>	<b>76.9</b>	<b>55.1</b>				
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.582	88.5	78.9	57.1				
Lower Limit		1.482	78.5	74.9	53.1				

\* Indicates result outside tolerance limits.



Test not Required by AT

PER: \_\_\_\_\_ **14-Jun-24**  
 DATE

Reviewed By: \_\_\_\_\_

Reporting of these results constitutes a testing service only.  
 Engineering Interpretation or evaluation of the test results is provided only on written request.