

TRAFFIC PAINT TEST REPORT

Project No.: EA16450




Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3

Distribution Addressee: WSP E&I Canada Limited
 5671 - 70 Street
 Edmonton, AB
 Canada T6B 3P6
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599

Formulation:		Supplier: PPG							
Yellow WB EF-62-0139		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch (Minutes)	Date Sampled	Date Received	Applicator and Location
B12	CPP2405W0519	1.562	75.2	76.5	55.4	3.2	Jun-6	Jun-7	Volker Stevin Taber Hwy 3:10
Tolerance Limits									
2023	EF-62-0139	1.576	78.6	77.3	55.4				
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.626	83.6	79.3	57.4				
Lower Limit		1.526	73.6	75.3	53.4				

* Indicates result outside tolerance limits.



Test not Required by AT

PER: _____ **24-Jun-24**

DATE

Reviewed By: _____

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.