

**TRAFFIC PAINT TEST REPORT**

Project No.: EA16450



Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation  
 Technical Standards Branch  
 2nd Floor, Twin Atria Building  
 4999 - 98 Ave  
 Edmonton, AB T6B 2X3

Distribution Addressee: WSP Canada Limited  
 5671 - 70 Street  
 Edmonton, AB  
 Canada T6B 3P6  
 Tel +1 (780) 436-2152  
 Fax +1 (780) 377-3599

Formulation: Yellow WB EF-62-0140		Supplier: PPG Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch (Minutes)	Date Sampled 2024	Date Received 2024	Applicator and Location
<b>B137</b>	CPP2407Y0800	1.599	86.7*	77.1	59.8	2.6	Sep-26	Oct-9	Line West Median Widening BeddingtonTr to Airport Trail Con#23525
<b>Tolerance Limits</b>									
<b>2023</b>	<b>EF-62-0140</b>	<b>1.649</b>	<b>79</b>	<b>76.6</b>	<b>60.4</b>	<b>2.4</b>			
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute	+2			
Upper Limit		1.699	84	78.6	62.4	4.4			
Lower Limit		1.599	74	74.6	58.4	N/A			

\* Indicates result outside tolerance limits.



Test not Required by AT

PER: \_\_\_\_\_ **28-Oct-24**

DATE

Reviewed By: \_\_\_\_\_

Reporting of these results constitutes a testing service only.  
 Engineering Interpretation or evaluation of the test results is provided only on written request.